of steel from this era or was steel fairly standardized by then where I could just use typical specification properties?

ASTM A94 steel, also historically known as silicon steel, was one of the first high-strength steels. Silicon contributes to the strength and hardness, but also reduces weldability. Silicon steel typically had a yield strength of 45 ksi, a tensile strength of 80-95 ksi and contained very little carbon. It was used in steel bridges and incorporated into the lower portions of built-up columns in buildings back in the 1910s and 1920s.

Material testing may be required. Appendix 5 in AISC 360-10, *Specification for Structural Steel Buildings*, provides information on the evaluation of existing structures, and provides provisions you might use to evaluate your structure. The document is available as free download at **www.aisc.org/freepubs**.

Erin Criste

PJP Groove Weld Strength

AISC *Specification* Table J2.5, Available Strength of Welded Joints, lists different PJP groove weld strengths in compression for "connections of members designed to bear other than columns" and "connections not finished-to-bear." Please explain what is meant by that and why the "connections not finished-to-bear" have a higher strength.

AISC *Specification* Table J2.5 covers three types of joints for PJP groove welds that transfer compression forces perpendicular to the weld axis: those in joints designed to bear and those in joints not designed to bear.

The first two types listed in the table are for joints designed to bear and refer to Section J1.4. Joints designed to bear are designed to transfer forces through steel-to-steel bearing. In other words, the PJP groove weld is not necessary to transfer compression forces. In the case of column splices or bases (J1.4a) the welds are there simply to hold the parts in place and compression in the weld does not need to be considered. In the case of joints in compression members other than columns (J1.4b), there are minimum lateral force or tensile requirements on the joint, thus the typical PJP groove weld strength is given equal to $0.6F_{exx}$.

The final case is for joints that are not designed to bear. In